

EMI 2561

(PC+ABS)-MEF(x)

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2758	MPa	ASTM D 638
Tensile Strength	58.6	MPa	ASTM D 638
Elongation at Break	8	%	ASTM D 638
Flexural Modulus	3103	MPa	ASTM D 790
Flexural Strength	103	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	10000	Ohm	ASTM D 257
Volume Resistivity	10	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	93.3	°C	-
Pre-drying - Time	4	h	-
Melt temperature	243 - 274	°C	-
Mold temperature	51.7 - 93.3	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Increased electrical conductivity

Features

EMI Attenuation/Shielding

Regional Availability

North America, Europe, Asia Pacific