

Product Texts

PBT 30% glass fibre reinforced injection moulding grade. Black colour.

Suitable for parts requiring high stiffness and good mechanical resistance.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9600	MPa	ISO 527
^[C] Stress at break	135	MPa	ISO 527
^[C] Strain at break	2.7	%	ISO 527
^[C] Charpy impact strength, +23°C	55	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	48	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	210	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	27	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	125	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
^[C] Comparative tracking index	350	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.3	%	Sim. to ISO 62
^[C] Humidity absorption	0.1	%	Sim. to ISO 62
^[C] Density	1530	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Additives

Release agent

Delivery form

Granules, Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

The material is delivered in moisture-proof packaging. It is important to dry the material prior to processing: maximum recommended water content is 0.02%. Typical conditions with a desiccant drier: temperature 120 ° C, dew point -40 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
250 - 280°C

Mold Temperature
80 - 90°C

Injection Speed
medium-high