

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	20	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10000	MPa	ISO 527
<sup>[C]</sup> Stress at break	130	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	55	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	50	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	207	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	218	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	223	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Oxygen index	20	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	300	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	1500	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa