

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	9500	MPa	ISO 527
Tensile Strength	150	MPa	ISO 527
Flexural modulus	8500	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Vicat softening temperature, B	190	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Electric strength	33	kV/mm	IEC 60243-1
Comparative tracking index	500	-	IEC 60112
<b>Other properties</b>			
Density	1550	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.1	%	-

## Characteristics

### Processing

Injection Molding

### Delivery form

Natural Color

### Special Characteristics

U.V. stabilized or stable to weather

### Applications

Automotive, Electrical and Electronical

### Regional Availability

Europe