

4DUR 9K23100 HI

PBT

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Stress at break	45	MPa	ISO 527
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Izod notched impact strength	6	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2
Vicat softening temperature, B	75	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1400	kg/m ³	ISO 1183
Moisture Content	0.08	%	-

Characteristics**Special Characteristics**

Flame retardant, High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

Europe