

**Product Texts**

Flame Retardant

ISO 1043 PBT FR

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>48</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>240</b>	°C	-
Load	<b>2.16</b>	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	<b>2.7</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>2.9</b>	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>3000</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>60</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>3</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>24</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>2</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>225</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>60</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>145</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1450</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Delivery form**

Pellets

**Regional Availability**

Asia Pacific

**Additives**

Release agent

**Other text information**

**Injection molding**

[Injection Molding Recommendations](#)

[Steel recommendations for molds screws and barrels](#)

[Supporting document for Stanyl quality processing](#)