

**Product Texts**

High Viscosity, Injection Molding, Extrusion, Food Contact Quality

ISO 1043 PBT

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>10</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>250</b>	°C	-
Load	<b>2.16</b>	kg	-
<sup>[C]</sup> Density of melt	<b>1040</b>	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	<b>0.109</b>	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	<b>2260</b>	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	<b>4.65E-8</b>	m <sup>2</sup> /s	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2550</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>55</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>3.5</b>	%	ISO 527
<sup>[C]</sup> Nominal strain at break	<b>&gt;50</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>225</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>55</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>170</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>90</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>90</b>	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>3.5</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>3.2</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>20</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>200</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	<b>27</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>600</b>	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.45</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.18</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1300</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

## Arnite® T08 200 (extrusion)

PBT

Envalior

### Processing

Injection Molding, Film Extrusion, Other Extrusion

### Certifications

Food contact

### Delivery form

Pellets

### Regional Availability

Europe, Asia Pacific

### Other text information

#### Injection molding

[Steel recommendations for molds screws and barrels](#)

[Supporting document for Stanyl quality processing](#)

#### Film extrusion

[Extrusion Guideline for Arnite® T-grades](#)