

**Product Texts**

Celanex 1700FC is a very high molecular weight extrusion grade of unreinforced polybutylene terephthalate for use in food contact applications.

Flammability at thickness h (0.75 HB mm)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	4.5	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2500	MPa	ISO 527
<sup>[C]</sup> Yield stress	60	MPa	ISO 527
<sup>[C]</sup> Yield strain	6	%	ISO 527
<sup>[C]</sup> Nominal strain at break	>50	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	220	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	7.5	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	7	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Shore D hardness	80	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	60	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	182	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	92	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<sup>[C]</sup> Oxygen index	22	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	4	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.6	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	14	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	210	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	>1E15	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	23	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.45	%	Sim. to ISO 62

**CELANEX® 1700FC**

PBT

Celanese

[C] Humidity absorption	<b>0.2</b>	%	Sim. to ISO 62
[C] Density	<b>1310</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion

**Delivery form**

Pellets

**Certifications**

Food contact

**Regional Availability**

North America, Europe, Asia Pacific