

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2500	MPa	ISO 527
^[C] Yield stress	60	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	190	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	190	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.25	%	Sim. to ISO 62
^[C] Density	1310	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Other Extrusion

Additives

Lubricants, Release agent

Delivery form

Pellets