

CELANEX® 3202-2LM

PBT

Celanese

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Stress at break	112	MPa	ISO 527
^[C] Strain at break	3.1	%	ISO 527

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Humidity absorption	0.1	%	Sim. to ISO 62
^[C] Density	1450	kg/m ³	ISO 1183

[C]: CAMPUS