

## Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

**Crastin® S620F20 NC010 is an unreinforced, nucleated, lubricated, medium viscosity polybutylene terephthalate resin for fast injection molding.**

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	1.7	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.6	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1110	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.21	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2100	J/(kg K)	-
<sup>[C]</sup> Ejection temperature	170	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2600	MPa	ISO 527
<sup>[C]</sup> Yield stress	59	MPa	ISO 527
<sup>[C]</sup> Yield strain	8	%	ISO 527
<sup>[C]</sup> Nominal strain at break	30	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	2600	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	1800	MPa	ISO 899-1
<sup>[C]</sup> Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	4.5	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	3.5	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	55	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	145	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	175	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	130	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	130	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
<sup>[C]</sup> Oxygen index	22	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	20	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	26	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.4	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.2	%	Sim. to ISO 62
<sup>[C]</sup> Density	1310	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	130	cm <sup>3</sup> /g	ISO 307, 1157, 1628

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Features

Nucleated

### Delivery form

Pellets, Natural Color

### Regional Availability

North America, Europe, Asia Pacific, South and Central America

### Additives

Lubricants, Release agent