

**DURANEX® 201AC**

PBT

Polyplastics

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>60</b>	MPa	ISO 527
Nominal strain at break	<b>45</b>	%	ISO 527
Flexural modulus, 23°C	<b>2410</b>	MPa	ISO 178
Flexural strength	<b>86</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>3.3</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	<b>M 90</b>	-	ISO 2039-2
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>70</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>110</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>110</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	<b>6E14</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>17</b>	kV/mm	IEC 60243-1
<b>Other properties</b>			
Density	<b>1310</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Asia Pacific