

DURANEX® 300FP

PBT

Polyplastics

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	35	°C	ISO 11357-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1310	kg/m ³	ISO 1183

Characteristics**Processing**

Film Extrusion, Other Extrusion

Regional Availability

Asia Pacific