

**Edgetek™ ET3300-0030 RS White**

PBT

Avient Corporation

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>7310</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>82.7</b>	MPa	ASTM D 638
Elongation at Break	<b>3</b>	%	ASTM D 638
Flexural Modulus	<b>6550</b>	MPa	ASTM D 790
Flexural Strength	<b>138</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>91</b>	J/m	ASTM D 256

  

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1470</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Pellets, White

**Special Characteristics**

Heat stabilized or stable to heat

**Chemical Resistance**

General Chemical Resistance

**Applications**

Automotive, Encapsulation

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa