

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000	MPa	ISO 527
Stress at break	36	MPa	ISO 527
Strain at break	10	%	ISO 527
Charpy impact strength, +23°C	25	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	2.5	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	2300	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Regional Availability

Europe

#### Applications

Automotive, Electrical and Electronical, Packaging, Sports Equipment