

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	13300	MPa	ISO 527
Stress at break	95	MPa	ISO 527
Strain at break	1.5	%	ISO 527
Charpy impact strength, +23°C	30	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1680	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Applications

Automotive, Encapsulation

Special Characteristics

Thermally Conductive

Regional Availability

Europe