

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	74	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	3100	MPa	ISO 178
Charpy notched impact strength, +23°C	2.5	kJ/m ²	ISO 179/1eA
Rockwell hardness	R119	-	ISO 2039-2
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Electric strength	20	kV/mm	IEC 60243-1
ASTM Data			
Dissipation Factor, 60 Hz	0.007	-	ASTM D 150
Dielectric Constant, 60 Hz	3.3	-	ASTM D 150
Other properties			
Density	1460	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120 - 130	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.05	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	230	°C	-
Zone 2	245	°C	-
Zone 3	235	°C	-
Nozzle temperature	245	°C	-
Screw speed	80 - 120	rpm	-
Back pressure	0.5 - 1	MPa	-

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

Flame retardant

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific