

NOVADURAN 5010N6 3X

PBT

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	20	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data	Value	Unit	Test Standard
Tensile Modulus	2800	MPa	ISO 527
Yield stress	57	MPa	ISO 527
Yield strain	4.3	%	ISO 527
Strain at break	20	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Charpy impact strength, +23°C	120	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data	Value	Unit	Test Standard
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	77	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.7	mm	-
Yellow Card available	yes	-	-
Electrical properties			
ISO Data	Value	Unit	Test Standard
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	21	kV/mm	IEC 60243-1
Comparative tracking index	500	-	IEC 60112
Other properties			
Value	Unit	Test Standard	
Water absorption	0.08	%	Sim. to ISO 62
Density	1430	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Value	Unit	Test Standard	
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Mold temperature	60 - 100	°C	-
Zone 1	240 - 260	°C	-
Zone 2	240 - 260	°C	-
Zone 3	240 - 260	°C	-
Nozzle temperature	260	°C	-
Screw speed	80 - 120	rpm	-
Injection pressure	20 - 150	MPa	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant

Applications

Automotive, Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa