

NOVADURAN 5010TR X5

PBT

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	14	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	1.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2340	MPa	ISO 527
Yield stress	47	MPa	ISO 527
Yield strain	3.1	%	ISO 527
Strain at break	140	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Flexural strength	70	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	155	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.4	-	IEC 62631-2-1
Dissipation factor, 1MHz	270	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	5E15	Ohm	IEC 62631-3-2
Electric strength	23	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Water absorption	0.1	%	Sim. to ISO 62
Density	1260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Mold temperature	60 - 80	°C	-
Zone 1	235	°C	-
Zone 2	240	°C	-
Zone 3	250	°C	-
Nozzle temperature	245	°C	-
Screw speed	80 - 150	rpm	-
Injection pressure	20 - 150	MPa	-

Characteristics

NOVADURAN 5010TR X5

PBT

Mitsubishi Engineering-Plastics Corporation

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Applications

Automotive, Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa