

PBT-R0N

PBT

Kingfa Sci. & Tech.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.013	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	50	MPa	ASTM D 638
Elongation at Break	25	%	ASTM D 638
Flexural Modulus	2500	MPa	ASTM D 790
Flexural Strength	65	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Izod Impact notched, 1/8 in	62.5	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
DTUL @ 66 psi	162	°C	ASTM D 648
DTUL @ 264 psi	63	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.06	%	ASTM D 570
Density	1430	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant, High impact or impact modified

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical

Regional Availability

Asia Pacific