

PIBITER N100

PBT

Celanese

Product Texts

PBT unreinforced, medium flowability

Flammability @0.8mm nom. HB
thickn. -

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2500	MPa	ISO 527
^[C] Yield stress	50	MPa	ISO 527
^[C] Yield strain	5	%	ISO 527

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1310	kg/m ³	ISO 1183

[C]: CAMPUS