

**PIBITER N200**

PBT

Celanese

**Product Texts**Flammability @0.8mm nom. HB  
thickn.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2500</b>	MPa	ISO 527
<sup>[C]</sup> Yield stress	<b>50</b>	MPa	ISO 527
<sup>[C]</sup> Yield strain	<b>5</b>	%	ISO 527

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1310</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS