

PIBITER N200LP

PBT

Celanese

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 2400 | MPa | ISO 527 |
| ^[C] Yield stress | 50 | MPa | ISO 527 |
| ^[C] Yield strain | 5 | % | ISO 527 |
| ^[C] Charpy notched impact strength, +23°C | 2 | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| ^[C] Density | 1320 | kg/m ³ | ISO 1183 |

[C]: CAMPUS