

**RamSter PF713GR356**

PBT

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>26</b>	g/10min	ISO 1133
Temperature	<b>250</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Other Standards<sup>[S]</sup></b>			
Molding shrinkage, parallel	<b>1.8</b>	%	Producer Method

S: These properties are reported by the producer according standards that are different to our defaults.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>2600</b>	MPa	ISO 527
Tensile Strength	<b>57</b>	MPa	ISO 527
Yield strain	<b>3.7</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>4.5</b>	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Humidity absorption	<b>0.25</b>	%	Sim. to ISO 62
Density	<b>1310</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>3 - 4</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Mold temperature	<b>70 - 90</b>	°C	-
Feed temperature	<b>40 - 60</b>	°C	-
Zone 1	<b>235 - 255</b>	°C	-
Zone 2	<b>235 - 255</b>	°C	-
Zone 3	<b>240 - 260</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

U.V. stabilized or stable to weather

**Certifications**

RoHS compliant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa