

Product Texts

Easy flow PBT for great flow path-wall thickness ratio

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	55	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Yield stress	55	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1310	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	250 - 260	°C	-
Mold temperature	70 - 90	°C	-

Characteristics**Processing**

Injection Molding

Additives

Release agent, Plasticizer

Delivery form

Granules

Regional AvailabilityNorth America, Europe, Asia Pacific, South and Central America,
Near East/Africa**Other text information****Injection molding**PREPROCESSING; **Pretreatment**

Predrying: 2-4 h / 120°C

PROCESSING ;**Processing:**

Melttemperature	250 - 260	°C
Mouldtemperature	70 - 90	°C