

**Tarolox 10 Z3**

PBT

Taro Plast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1900	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	600	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Vicat softening temperature, A	158	°C	ISO 306
Vicat softening temperature, B	135	°C	ISO 306
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
<b>Other properties</b>			
Water absorption	0.3	%	Sim. to ISO 62
Density	1250	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Pellets

**Features**

Low Odor

**Additives**

Release agent

**Regional Availability**

Europe

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat