

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Tensile Strength	50	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Charpy impact strength, +23°C	290	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6.2	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 70	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	140	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	19	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	1290	kg/m ³	ISO 1183

Characteristics

Special Characteristics

High impact or impact modified

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa