

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>10000</b>	MPa	ISO 527
Tensile Strength	<b>135</b>	MPa	ISO 527
Strain at break	<b>2.2</b>	%	ISO 527
Flexural modulus, 23°C	<b>10000</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>9.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>163</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>209</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>42</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
<b>Electrical properties</b>			
<b>ISO Data</b>			
Dissipation factor, 1MHz	<b>100</b>	E-4	IEC 62631-2-1
Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>16</b>	kV/mm	IEC 60243-1
<b>Other properties</b>			
Density	<b>1390</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Features**

Low Warpage

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa