

Product Texts

Injection Molding, Unreinforced, Extrusion, Food Contact Quality

ISO 1043 PBT

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	14	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2600	MPa	ISO 527
^[C] Yield stress	55	MPa	ISO 527
^[C] Yield strain	4	%	ISO 527
^[C] Nominal strain at break	>50	%	ISO 527
^[C] Tensile creep modulus, 1h	2200	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	1300	MPa	ISO 899-1
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	200	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA
^[C] Puncture - maximum force, +23°C	3710	N	ISO 6603-2
^[C] Puncture - maximum force, -30°C	4280	N	ISO 6603-2
^[C] Puncture energy, +23°C	44	J	ISO 6603-2
^[C] Puncture energy, -30°C	23	J	ISO 6603-2

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	130	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
^[C] Burning rate, FMVSS, Thickness 1 mm	9	mm/min	ISO 3795 (FMVSS 302)
^[C] Oxygen index	24	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.4	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	15	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	30	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.5	%	Sim. to ISO 62
^[C] Humidity absorption	0.2	%	Sim. to ISO 62

Pocan® B1600 000000

PBT-I

Envalior

^[C] Density	1300	kg/m ³	ISO 1183
^[C] : CAMPUS			

Material specific properties	Value	Unit	Test Standard
------------------------------	-------	------	---------------

ISO Data

^[C] Viscosity number	140	cm ³ /g	ISO 307, 1157, 1628
---------------------------------	------------	--------------------	---------------------

^[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
--------------------------	-------	------	---------------

ISO Data

^[C] Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

^[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
---	-------	------	---------------

Pre-drying - Temperature	120	°C	-
--------------------------	------------	----	---

Pre-drying - Time	4 - 8	h	-
-------------------	--------------	---	---

Processing humidity	≤0.02	%	-
---------------------	--------------	---	---

Characteristics**Processing**

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion, Coating

Certifications

Food contact

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

High impact or impact modified

Other text information**Injection molding**

PREPROCESSING

Residual moisture content: 0.00 - 0.02 %

Drying temperature circulating air dryer: 120 °C

Drying time circulating air dryer: 4 - 8 h

PROCESSING