

Carbotex K-30CF10

PC-CF10

Kotec Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Break	118	MPa	ASTM D 638
Elongation at Break	118	%	ASTM D 638
Flexural Modulus	5700	MPa	ASTM D 790
Flexural Strength	150	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
DTUL @ 264 psi	147	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	110	s	ASTM D 495
Other properties			
Water Absorption, 24hr	0.2	%	ASTM D 570
Density	1240	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets, Black, Natural Color

Regional Availability

North America, Europe, Near East/Africa

Features

Low Odor