

ComAlloy 510-3010

PC-GF10

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	62.1	MPa	ASTM D 638
Flexural Modulus	3792	MPa	ASTM D 790
Flexural Strength	103	MPa	ASTM D 790
Izod Impact notched, 1/8 in	267	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	143	°C	ASTM D 648
DTUL @ 264 psi	138	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1250	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America