

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	50	MPa	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	5	%	ISO 527
Flexural modulus, 23°C	3200	MPa	ISO 178
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Izod notched impact strength	4	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	130	°C	ISO 75-1/-2
Vicat softening temperature, A	145	°C	ISO 306
Vicat softening temperature, B	138	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Other properties			
Density	1250	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Flame retardant

Regional Availability

Europe