

4LEX 9F12120

PC-GF20

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	6	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	6500	MPa	ISO 527
Stress at break	115	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod notched impact strength, +23°C	12	kJ/m ²	ISO 180/1A
Izod notched impact strength	10	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	140	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	145	°C	ISO 75-1/-2
Vicat softening temperature, B	145	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Comparative tracking index	175	-	IEC 60112
Other properties			
Density	1330	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics**Regional Availability**

Europe