

Iupilon EGN2020DF

PC-GF20

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Stress at break	74	MPa	ISO 527
Strain at break	3.7	%	ISO 527
Flexural modulus, 23°C	5000	MPa	ISO 178
Flexural strength	117	MPa	ISO 178
Charpy impact strength, +23°C	36	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	133	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	139	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-
Electrical properties			
ISO Data			
Comparative tracking index	212	-	IEC 60112
Other properties			
Water absorption	0.11	%	Sim. to ISO 62
Density	1350	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-
Mold temperature	80 - 120	°C	-
Zone 1	280 - 300	°C	-
Zone 2	280 - 300	°C	-
Zone 3	280 - 300	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant, Phosphorus-free

Features

Low Warpage

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa