

Iupilon GSH2020DR 9913A

PC-GF20

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	6.5	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Melt flow index, MFI	7.6	g/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6200	MPa	ISO 527
Stress at break	86	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Flexural modulus, 23°C	5500	MPa	ISO 178
Flexural strength	141	MPa	ISO 178
Charpy impact strength, +23°C	43	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	136	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	140	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	62	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Yellow Card available	yes	-	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	212	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	0.11	%	Sim. to ISO 62
Density	1350	kg/m ³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 8	h	-
Mold temperature	80 - 120	°C	-
Zone 1	290 - 310	°C	-
Zone 2	290 - 310	°C	-
Zone 3	290 - 310	°C	-
Nozzle temperature	290 - 310	°C	-

Characteristics**Processing**

Coating

Applications

IT / Business Machine

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa