

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>14</b>	g/10min	ASTM D 1238
Temperature	<b>300</b>	°C	-
Load	<b>1.2</b>	kg	-
Mold Shrinkage, MD	<b>0.003</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile Strength	<b>102</b>	MPa	ASTM D 638
Flexural Modulus	<b>6757</b>	MPa	ASTM D 790
Flexural Strength	<b>159</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 110</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>96.1</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>135</b>	°C	ASTM D 648
<b>Other properties</b>			
<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>	
Density	<b>1420</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Special Characteristics**

Flame retardant

**Certifications**

RoHS compliant

**Applications**

IT / Business Machine

**Regional Availability**

Europe, Asia Pacific