

**Product Texts**

LNP THERMOCOMP DF004 compound is based on Polycarbonate (PC) resin containing 20% glass fiber.

UL Yellow Card Link [E207780-101343856](https://www.ul.com/yellow-card/E207780-101343856)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.5	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	6000	MPa	ISO 527
Stress at break	102	MPa	ISO 527
Strain at break	8	%	ISO 527
Flexural modulus	6000	MPa	ISO 178
Flexural strength	148	MPa	ISO 178
Izod impact strength, +23°C, 4mm	61	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	8	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	5510	MPa	ASTM D 638
Tensile Strength at Break	91	MPa	ASTM D 638
Elongation at Break	9.5	%	ASTM D 638
Flexural Modulus	5510	MPa	ASTM D 790
Flexural Strength	149	MPa	ASTM D 790
Izod Impact notched, 1/8 in	133	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	961	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	142	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	144	°C	ASTM D 648
DTUL @ 264 psi	139	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m <sup>3</sup>	ISO 1183
Water Absorption, 24hr	0.1	%	ASTM D 570
Density	1350	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

Asia Pacific