

LUPOY GP2200

PC-GF20

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	98.1	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Flexural Modulus	5395	MPa	ASTM D 790
Flexural Strength	157	MPa	ASTM D 790
Rockwell Hardness	R 122	-	ASTM D 785
Izod Impact notched, 1/8 in	94.3	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	140	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100 - 120	°C	-
Pre-drying - Time	3 - 5	h	-
Processing humidity	≤0.02	%	-
Melt temperature	300 - 340	°C	-
Mold temperature	90 - 120	°C	-
Zone 1	270 - 300	°C	-
Zone 2	280 - 310	°C	-
Zone 3	290 - 330	°C	-
Nozzle temperature	290 - 330	°C	-
Screw speed	40 - 70	rpm	-
Back pressure	1 - 4	MPa	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Applications

Automotive, IT / Business Machine, Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific, South and Central America