

PCG-2200

PC-GF20

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	103	MPa	ASTM D 638
Flexural Modulus	5396	MPa	ASTM D 790
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	140	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1330	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	300 - 320	°C	-
Mold temperature	80 - 110	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	280 - 300	°C	-
Zone 2	290 - 310	°C	-
Zone 3	300 - 320	°C	-
Nozzle temperature	290 - 310	°C	-

Characteristics**Processing**

Injection Molding

Additives

Release agent

Special Characteristics

High impact or impact modified

Applications

Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific