

PCG-2205

PC-GF20

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	88.3	MPa	ASTM D 638
Flexural Modulus	5396	MPa	ASTM D 790
Izod Impact notched, 1/8 in	108	J/m	ASTM D 256
Thermal properties			
ISO Data			
Burning behav. 5V at thickness h	5VA	class	IEC 60695-11-20
Thickness tested	3.0	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	140	°C	ASTM D 648
Other properties			
Density	1350	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	300 - 320	°C	-
Mold temperature	80 - 110	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	280 - 300	°C	-
Zone 2	290 - 310	°C	-
Zone 3	300 - 320	°C	-
Nozzle temperature	290 - 310	°C	-

Characteristics**Processing**

Injection Molding

Additives

Release agent

Special Characteristics

Flame retardant, Halogen-free, High impact or impact modified

Applications

Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific