

**Product Texts**

Base Polymer	Polycarbonate
Filler/Additive System	30 % glass fibres
Special Features	good flow
Market Segment	Automotive,electrical and electronic
Typical Applications	thin walled parts,housings

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	15	cm <sup>3</sup> /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

[C]: CAMPUS

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	6300	MPa	ISO 527
<sup>[C]</sup> Stress at break	75	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.4	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	40	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	139	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	144	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

**Other properties**

	Value	Unit	Test Standard
<sup>[C]</sup> Density	1420	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific, Near East/Africa

**Other text information****Injection molding**

Pre-Drying Conditions      120 °C in a dry air (dessiccant) dryer  
for 2-3 h  
120 °C in an air circulating dryer  
for 4-12 h  
dependant on moisture content  
max. moisture content <0,02 %

Processing Injection Moulding      melt temperature 270-310 °C  
mould temperature 80-110 °C

Storage      dry, protected from light