

Product Texts

LNP THERMOCOMP DX13354 compound is based on Polycarbonate (PC) resin containing 30% glass fiber. Added features of this grade include: Improved Plating Surface and Mechanical Performance suitable for Laser Direct Structuring (LDS) applications, Improved Impact, Good Surface Aesthetics and Wide Processing Window.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	16	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8840	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Flexural modulus	8450	MPa	ISO 178
Flexural strength	180	MPa	ISO 178
Izod impact strength, +23°C, 4mm	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	14	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	8760	MPa	ASTM D 638
Tensile Strength at Break	120	MPa	ASTM D 638
Elongation at Break	2.4	%	ASTM D 638
Flexural Modulus	8020	MPa	ASTM D 790
Flexural Strength	170	MPa	ASTM D 790
Izod Impact notched, 1/8 in	150	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	700	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	124	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	127	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	126	°C	ASTM D 648
DTUL @ 264 psi	122	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1470	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	270 - 295	°C	-
Mold temperature	100 - 120	°C	-
Zone 1	270 - 295	°C	-
Zone 2	270 - 295	°C	-
Zone 3	270 - 295	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Applications

Automotive