

XYRON™ AF700

(PA66+PPE)

Asahi Kasei

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1120	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa