

PERLEX® R2530

PC-GF30

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8400	MPa	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	143	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	149	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	145	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1350	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa