

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8400	MPa	ISO 527
^[C] : CAMPUS			

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	143	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	149	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	145	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn. Thickness tested	V-0 1.6	class mm	IEC 60695-11-10 -
^[C] Burning Behav. at thickness h Thickness tested	V-0 3.2	class mm	IEC 60695-11-10 -
^[C] : CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Density	1350	kg/m ³	ISO 1183
^[C] : CAMPUS			

Characteristics

Special Characteristics

Flame retardant

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa