

TRISTAR® PC-30GF-(U)

PC-GF30

Amco Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	128	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	7584	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	143	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1430	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Additives

Release agent

Certifications

RoHS compliant

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa