

Product Texts

30% Glass Reinforced, Flame Retardant, UV Stabilized

ISO 1043 PC-GF30 FR

[XANTAR Polycarbonate & Blends, your global partner for innovative added value](#)

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	4	cm ³ /10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.4	%	ISO 294-4, 2577
^[C] Density of melt	1220	kg/m ³	-
^[C] Thermal conductivity of melt	0.32	W/(m K)	-
^[C] Spec. heat capacity of melt	1440	J/(kg K)	-
^[C] Eff. thermal diffusivity	1.53E-7	m ² /s	-
^[C] Ejection temperature	144	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9500	MPa	ISO 527
^[C] Stress at break	110	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	145	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	152	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
Yellow Card available	yes	-	-
^[C] Oxygen index	36	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.4	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.4	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	9	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	90	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	29	kV/mm	IEC 60243-1
^[C] Comparative tracking index	200	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.26	%	Sim. to ISO 62
^[C] Density	1430	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	100	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.03	%	-
Melt temperature	290 - 320	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	260 - 280	°C	-
Zone 2	270 - 290	°C	-
Zone 3	280 - 300	°C	-
Nozzle temperature	270 - 290	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Release agent

Special Characteristics

Flame retardant, Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Europe

Other text information

Injection molding

[Injection Molding Recommendations](#)