

Product Texts

LNP THERMOCOMP DF00A8P compound is based on Polycarbonate (PC) resin containing 50% glass fiber. Added features of this grade include: High Modulus, Low Warpage, Improved Impact performance, Non-Brominated & Non-Chlorinated Flame Retardant.

UL Yellow Card Link [E207780-101219669](https://www.ul.com/yellowcard/E207780-101219669)

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.125	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.125	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	15100	MPa	ISO 527
Stress at break	153	MPa	ISO 527
Strain at break	1.9	%	ISO 527
Charpy impact strength, +23°C	38	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Modulus	15320	MPa	ASTM D 638
Tensile Strength at Break	154	MPa	ASTM D 638
Elongation at Break	2.1	%	ASTM D 638
Flexural Modulus	14870	MPa	ASTM D 790
Izod Impact notched, 1/8 in	127	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	520	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
ASTM Data			
DTUL @ 264 psi	107	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1640	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	110	°C	-
Pre-drying - Time	3 - 6	h	-
Processing humidity	≤0.02	%	-
Melt temperature	285 - 310	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	260 - 280	°C	-
Zone 2	270 - 290	°C	-
Zone 3	280 - 300	°C	-
Screw speed	50 - 90	rpm	-
Back pressure	0.1 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Additives

Flame retarding agent

Special Characteristics

Flame retardant

Regional Availability

North America, Europe, Asia Pacific