

**Product Texts**

Bioresorbablepolymers to enhance the performance of medical devices.

Degradation timeframe: > 2 years

Applications: orthopedic, cardiovascular, wound healing

Inherent viscosity range: 0,8-1,2 dL/g

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	65	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	-62	°C	ISO 11357-1/-2

**Characteristics****Special Characteristics**

Sterilizable, Ethylene Oxide (EtO) Sterilization, Gamma irradiation sterilization, Electron beam (e-beam) sterilization

**Certifications**

Contains renewable resources, Biodegradable, Medical Grade, Drug Master File, Device Master File

**Applications**

Medical

**Regional Availability**

Europe