

EMI 360.5 FR

PC-MEF(x)5

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	2413	MPa	ASTM D 638
Tensile Strength	58.6	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	89.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256
Electrical properties			
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Volume Resistivity	1000	Ohm*cm	ASTM D 257
Other properties			
Density	1290	kg/m ³	ASTM D 792
Moisture Content	0.02	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	277 - 304	°C	-
Mold temperature	71.1 - 121	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Features

EMI Attenuation/Shielding

Special Characteristics

Increased electrical conductivity, Flame retardant

Regional Availability

North America, Europe, Asia Pacific